

DOUBLE PROTECTION

# With the innovative JuraGal® Platinum Coating

High Strength Steel and Now More Durable





# **OZPROFILE<sup>™</sup> WITH THE DURAGAL® PLATINUM ADVANTAGE**

OZProfiles are high strength in-line open sections coated with the innovative DuraGal® Platinum hot-dip zinc aluminium coating, providing a smooth surface with a uniform coating thickness, purpose designed to perform in general, and construction applications.



## NOTE

\* Zinc aluminium coating classifications are not currently referenced in AS/NZS 4791, hot-dip galvanized (zinc) coatings on ferrous open sections applied by an in-line process.

You determine the design and specification, and let us provide a consistent coating!

# **DURAGAL® PLATINUM TECHNOLOGY**

The DuraGal<sup>®</sup> Platinum coating technology applies a hot-dip zinc aluminium coating using our innovative application process pioneered in Australia by OneSteel Australian Tube Mills. Our specialised application process and quality control procedures detailed in our Technical Specifications document, TS100 ensures that DuraGal® Platinum coated OZProfiles continue to be manufactured and inspected to the standards required by AS/NZS 4791:2006 — hot-dip galvanized (zinc) coatings on ferrous open sections, applied by an in-line process.

For further information or to review our manufacturing standard TS100 please visit www.austubemills.com

# **COST EFFECTIVE**

OZProfiles with the new DuraGal<sup>®</sup> Platinum coating are a cost-effective way to work with steel. As demonstrated in the graph, when it comes to achieving comparable levels of strength and surface protection, experience has shown that it can be more economical to simply switch to OZProfile sections, delivering greater value for money to help your business grow.

### **IDENTIFYING OPPORTUNITIES**

OZProfiles are versatile and can be adapted into all industries. Whether it be in mining, house frames, materials handling, racking (particularly in cold rooms) access walkways, truck & trailer bodies or transmission towers. Conversion to OZProfiles can save you time and money.

COST PER METRE

- 4. Reduced inventory no outsourcing means less stock in the system = space and cost savings
- 5. Kinder to the environment no wire brushing or priming pollutants
- 6. Reduced process time clean and better to handle
- 7. Availability stocked throughout the extensive OneSteel Australian Tube Mills distribution network
- 8. Lower total cost potential





#### **OZPROFILES VS A COMPARABLE PRIMED HOT ROLLED SECTION**



# **KEY BENEFITS OF USING OZPROFILES**

- 1. Quality improvement prepared surface and corrosion resistance can alleviate the need for blasting and priming
- 2. Lighter average 15% savings in weight less freight costs
- 3. Improved business management no outsourcing for coating preparation means less material management



# THE PERFECT **FINISHING TOUCH**

#### SURFACE PROTECTION

OZProfiles coated with DuraGal® Platinum now offers double the barrier against corrosion but still demonstrates the same processing capability end-users have grown to trust. DuraGal® Platinum's zinc aluminium coating applied in-line has an equivalent durability of a 225g/m<sup>2</sup> zinc coating, in moderate and severe environments.

OZProfiles surface finish is smooth, clean, free from oil, mill scale, rust and dirt making our range of Angles, Channels and Flats ready to use, so there is no need to waste time and money on shot blasting, wire brush cleaning or priming after fabrication.

#### **HIGH STRENGTH PERFORMANCE**

OZProfiles feature high tensile strength properties. Both Angles and Channels achieve up to 450 MPa, and Flats have a minimum yield strength rating of up to 400 MPa. So, in many applications, a lighter OZProfile may be substituted for Grade 250/300 hot rolled steel, without making any compromises in compression, tension or bending performance. Providing opportunities for significant reductions in material and fabrication costs.

#### **KINDER TO THE ENVIRONMENT**

Because OZProfiles don't need to be blasted, wire brushed or primed, the pollutants normally associated with these processes are a thing of the past. This is not only good news for you and your workforce, it's good news for the environment as well.

#### **HOW TO SPECIFY**

Specifying OZProfiles with a DuraGal<sup>®</sup> Platinum Coating is the only way to be sure you get what you need:

150 x 75 x 5.0 CC with a DuraGal<sup>®</sup> Platinum Coating.

#### WELDING PERFORMANCE

OZProfiles are made from low carbon structural steel, so they are readily weldable. The zinc coating thickness is carefully controlled to ensure that structurally sound welds can be fabricated using standard welding practices.

The 'DuraGal Easy Welding Guide' provides basic guidelines for welding DuraGal products. We recommend:

- Don't increase the heat
- Use the correct wire or rod
- Use a gas high in CO, content



# **A BETTER WAY OF WORKING WITH STEEL**

#### **INCREASE THE COATING** THICKNESS FOR IMPROVED **CORROSION PROTECTION**

For applications where superior corrosion performance is required - trusses, bracing, cold storage, transport frames and chassis or transmission towers — You can now specify OZProfiles with 200g/m<sup>2</sup> of DuraGal<sup>®</sup> Platinum. This coating provides equivalent durability of a 600g/m<sup>2</sup> zinc coating for a moderate and severe environment.

This means our selected range of OZProfiles Angles, Channels and Flats can now be considered for applications where compliance with AS/NZS 4680:2006 'Hot-dip galvanized (zinc) coatings on fabricated ferrous articles' is required.

#### NOTE

- 1. The surface appearance of our 200g/m<sup>2</sup> coating represents that of a typical hot-dipped galvanized coating. May not be suitable for aesthetic applications or where a precision top coat will be applied.
- 2. Weldability reduces, and weld fume increases at higher coating thicknesses. Variations to standard welding practices may be required to weld a 200g/m<sup>2</sup> coating.

### **COMPARISON RESULTS IN CORROSION TESTING**










Laboratory and field testing has demonstrated that the DuraGal® Platinum coating significantly exceeds the durability of a zinc coating with an equivalent mass in a range of different environments.



# SUGGESTED OZPROFILE APPLICATIONS


The smooth square profile allows easy connection in a variety of structural applications.



## RACKING

OZProfiles present unique attributes perfect for many industrial and materials handling applications. The illustration shows OZProfile Angles used as Pallet Racking Support Beams, where the shape, finish and strength are ideally suited.


OZProfile material thickness of 6mm and less can be used down to -30 degrees centigrade and above 6mm thickness for -20 degrees centigrade. This means OZProfiles are ideal for cold room storage applications.



### PORTABLE BUILDING CHASSIS

Portable Building Manufacturers are keenly aware of what products need to deliver to make it into their buildings. Products must satisfy design, plus additional demands of handling, transport and potentially corrosive environments.

OZProfiles are hard to beat, offering versatility, strength, durability and practicality.



### FLOORING SYSTEM

The factory applied durable coating and structurally efficient section properties of OZProfile Channels combined with simple bolted connections to create flooring solutions requiring minimal surface treatment and simple fabrication.

# OZPROFILE RANGE, STEEL GRADES AND AVAILABILITY

#### **OZPROFILE ANGLES**

Size		Standard	Nominal Thickness — mm										
			2.5	4.0	5.0	6.0	8.0						
		m	Grade	Grade	Grade	Grade	Grade	9	Sizes Stocked				
< 30	CA	6.0		-	-	-	-						
<b>‹</b> 40	CA	6.0	1.43 kg/m	2.20 kg/m	-	-	-	1	izes Subject to enquiry				
c 45	CA	6.0	1.62 kg/m	2.50 kg/m	-	-	-						
< 50	CA	6.0	1.81 kg/m	-	-	-	-		Other thicknesses & lengths subject to enquiry				
c 50	CA	9.0	-	2.79 kg/m	3.42 kg/m	4.21 kg/m	-						
c 65	CA	9.0	-	3.69 kg/m	4.52 kg/m	5.62 kg/m	-						
c 75	CA	9.0	-	4.29 kg/m	5.26 kg/m	6.56 kg/m	8.59 kg/m			Minimum	Minimum		
<b>&lt; 90</b>	CA	9.0	-	-	6.37 kg/m	-	10.5 kg/m	Grade	Minimum Yield Stress MPa	Tensile	Elongation as a Proportion of Gauge Length of 5.65 $\sqrt{S_o}$ (%)		
c 100	CA	12.0	-	-	-	8.92 kg/m	11.7 kg/m						
c 125	CA	12.0	-	7.27 kg/m	8.95 kg/m	-	14.9 kg/m	(13100)					
c 150	CA	12.0	-	-	10.8 kg/m	13.6 kg/m	18.0 kg/m						
< 50	CA	9.0	-	3.54 kg/m	4.34 kg/m	5.38 kg/m	-	C350L0	350	400	20		
x 75	CA	12.0	-	-	-	7.74 kg/m	10.2 kg/m						
x 75	CA	12.0	-	-	-	8.92 kg/m	11.7 kg/m	C400L0	400	450	16		
c 100	CA	12.0	-	-	-	11.3 kg/m	14.9 kg/m	C450L0	450	500	16		
	30 40 50 50 65 75 90 100 125 150 50 <75 <75	30     CA       40     CA       45     CA       50     CA       50     CA       50     CA       65     CA       90     CA       100     CA       125     CA       50     CA       50     CA       50     CA       65     CA       65     CA       75     CA       50     CA	Size     Length m       30     CA     6.0       40     CA     6.0       45     CA     6.0       50     CA     9.0       50     CA     9.0       65     CA     9.0       75     CA     9.0       100     CA     12.0       125     CA     12.0       50     CA     12.0       150     CA     12.0       50     CA     12.0	Length m     2.5       Grade C350L0     Grade C350L0       30     CA     6.0     1.06 kg/m       40     CA     6.0     1.43 kg/m       45     CA     6.0     1.62 kg/m       50     CA     9.0     -       65     CA     9.0     -       75     CA     9.0     -       90     CA     12.0     -       125     CA     12.0     -       150     CA     9.0     -       150     CA     12.0     -       150     CA     12.0     -       50     CA     12.0     -	Length m     2.5     4.0       Grade C350L0     Grade C450L0       30     CA     6.0     1.06 kg/m       40     CA     6.0     1.43 kg/m     2.20 kg/m       45     CA     6.0     1.62 kg/m     2.50 kg/m       50     CA     6.0     1.81 kg/m     2.20 kg/m       50     CA     9.0     1.62 kg/m     3.69 kg/m       50     CA     9.0     -     2.79 kg/m       65     CA     9.0     -     3.69 kg/m       90     CA     9.0     -     -       100     CA     12.0     -     -       125     CA     12.0     -     -       150     CA     12.0     -     -       50     CA     9.0     -     -       150     CA     12.0     -     -       50     CA     9.0     -     -       50     CA     12.0     -     -       57	Size     Length m     2.5     4.0     5.0       Grade C350L0     Grade C450L0     Grade C450L0     Grade C450L0     Grade C450L0       30     CA     6.0     1.06 kg/m     -     -       40     CA     6.0     1.43 kg/m     2.20 kg/m     -       45     CA     6.0     1.62 kg/m     2.50 kg/m     -       50     CA     6.0     1.81 kg/m     -     -       50     CA     9.0     -     2.79 kg/m     3.42 kg/m       65     CA     9.0     -     3.69 kg/m     4.52 kg/m       90     CA     9.0     -     -     6.37 kg/m       90     CA     9.0     -     -     -       100     CA     12.0     -     -     -       125     CA     12.0     -     -     -       150     CA     9.0     -     3.54 kg/m     4.34 kg/m       50     CA     9.0     -     -     -	Size     Length m     2.5     4.0     5.0     6.0       Grade C350L0     Grade C450L0     -	Size     Length m     2.5     4.0     5.0     6.0     8.0       Grade C350L0     Grade C450L0     Grade C400L0     Grade C400L0	Size     Length     2.5     4.0     5.0     6.0     8.0       Grade     Grade	Size     Length m     2.5     4.0     5.0     6.0     8.0       30     CA     6.0     1.06 kg/m     C450L0     C450L0     C450L0     C400L0       30     CA     6.0     1.06 kg/m     -     -     -     -       40     CA     6.0     1.43 kg/m     2.20 kg/m     -     -     -       45     CA     6.0     1.62 kg/m     2.50 kg/m     -     -     -       50     CA     6.0     1.81 kg/m     -     -     -     -       50     CA     9.0     -     2.79 kg/m     3.42 kg/m     4.21 kg/m     -     -       50     CA     9.0     -     2.79 kg/m     3.42 kg/m     5.62 kg/m     -     -       75     CA     9.0     -     3.69 kg/m     4.52 kg/m     5.62 kg/m     -     -       90     CA     9.0     -     6.37 kg/m     -     10.5 kg/m     10.5 kg/m       125     CA     12.0 </td <td>Size     Length m     2.5     4.0     5.0     6.0     8.0       30     CA     6.0     1.06 kg/m     Grade C450L0     Grade C450L0     Grade C450L0     Grade C450L0     Grade C400L0     Grade C400L0     Sizes Stocked       30     CA     6.0     1.06 kg/m     -     -     -     -       40     CA     6.0     1.43 kg/m     2.20 kg/m     -     -     -       45     CA     6.0     1.62 kg/m     2.50 kg/m     -     -     -     -       50     CA     6.0     1.81 kg/m     -     -     -     -     -       50     CA     9.0     -     2.79 kg/m     3.42 kg/m     4.21 kg/m     -     -     -     -     0ther thicknesses &amp; length subject to enquiry       50     CA     9.0     -     3.69 kg/m     5.52 kg/m     5.62 kg/m     -     10.5 kg/m       90     CA     9.0     -     6.37 kg/m     -     10.5 kg/m     -     10.5 kg/m  &lt;</td>	Size     Length m     2.5     4.0     5.0     6.0     8.0       30     CA     6.0     1.06 kg/m     Grade C450L0     Grade C450L0     Grade C450L0     Grade C450L0     Grade C400L0     Grade C400L0     Sizes Stocked       30     CA     6.0     1.06 kg/m     -     -     -     -       40     CA     6.0     1.43 kg/m     2.20 kg/m     -     -     -       45     CA     6.0     1.62 kg/m     2.50 kg/m     -     -     -     -       50     CA     6.0     1.81 kg/m     -     -     -     -     -       50     CA     9.0     -     2.79 kg/m     3.42 kg/m     4.21 kg/m     -     -     -     -     0ther thicknesses & length subject to enquiry       50     CA     9.0     -     3.69 kg/m     5.52 kg/m     5.62 kg/m     -     10.5 kg/m       90     CA     9.0     -     6.37 kg/m     -     10.5 kg/m     -     10.5 kg/m  <		

### **OZPROFILE CHANNELS**

		Standard	Nominal Thickness — mm						
Size		Length	4.0 5.0		6.0	8.0			
		m	Grade	Grade	Grade	Grade			
			C450L0	C450L0	C450L0	C400L0			
75 x 40	СС	9.0	4.25 kg/m						
100 x 50	СС	9.0	5.59 kg/m						
125 x 65	СС	9.0	7.23 kg/m						
150 x 75	CC	12.0		10.5 kg/m					
180 x 75	CC	12.0		11.6 kg/m					
200 x 75	СС	12.0		12.4 kg/m	15.5 kg/m				
230 x 75	CC	12.0			16.9 kg/m				
250 x 90	СС	12.0			19.2 kg/m				
300 x 90	CC	12.0			21.6 kg/m	28.5 kg/m			





### **OZPROFILE FLATS**

		Standard	Nominal Thickness — mm					
Size		Length	4.0 5.0		6.0	8.0		
5120		m		Grade	Grade	Grade		
			C400L0	C400L0	C400L0	C350L0		
50	CF	6.0	1.49 kg/m	1.84 kg/m	-	-		
65	CF	6.0	1.94 kg/m	2.40 kg/m	-	-		
75	CF	6.0	2.24 kg/m	2.77 kg/m	-	-		
90	CF	6.0	-	-	4.24 kg/m	-		
100	CF	6.0	2.98 kg/m	3.69 kg/m	4.71 kg/m	6.28 kg/m		
130	CF	6.0	-	4.80 kg/m	-			
150	CF	6.0	-	5.53 kg/m	7.07 kg/m	9.42 kg/m		
200	CF	6.0	-	7.38 kg/m	9.42 kg/m	12.6 kg/m		
250	CF	6.0	-	9.22 kg/m	-	15.7 kg/m		
300	CF	6.0	-	11.1 kg/m	-	18.8 kg/m		



OneSteel Australian Tube Mills 146 Ingram Road, Acacia Ridge Queensland 4110 Australia PO Box 246, Sunnybank Queensland 4109 Australia Phone: +61 7 3909 6600 Fax: +61 7 3909 6660 www.austubemills.com



DISTRIBUTED BY



This publication has been prepared as a guide only to assist anyone that may specify or use the products described in this publication. Accordingly, while OneSteel has endeavoured to ensure that all information provided in this publication is accurate and up-to-date, the following must be noted: this publication does not take into account any individual circumstances and is therefore not a substitute for informed or professional individual advice; the specifications and technical data relating to the products described in this publication are approximate and subject to change without notice, and users should check the currency of the information before relying upon it; and unless required by law, OneSteel does not accept any responsibility for any loss, damage or consequence resulting from the contents of this publication or from any omission of information in this publication. © Copyright OneSteel Australian Tube Mills Pty Ltd. DuraGal® Platinum, O2Profiles<sup>™</sup> and O2Lintel<sup>™</sup> are registered trade marks of OneSteel Australian Tube Mills Pty Ltd. June 2011. EMS5329.